



1560 Lisbon Street, Lewiston, Maine 04240

Telephone: 207-333-6100 • Toll Free: 800-343-8008 (USA)

www.elmettechnologies.com

Certified to ISO 9001 & 14001

MOLYBDENUM MOD METAL POWDER MATERIAL DATA SHEET

The chemical composition complies with ASTM requirements for powder lot analysis. Actual finished part chemical analysis and mechanical properties are not routinely evaluated per ASTM requirements. ASTM specifications and test methods are used as guidelines to control and monitor our processes to assure product quality. Applicable ASTM Material Standard: **none**.

This product meets the requirements of low copper and mercury-free materials.

CHEMICAL COMPOSITION			
Mo:(excluding gasses)	99.95% Min.	Na:	20 PPM Max.
Al:	50 PPM Max.	Ni:	50 PPM Max.
Cr:	20 PPM Max.	O:	0.1% Max.
Cu:	10 PPM Max.	Si:	50 PPM Max.
Fe:	50 PPM Max.	W:	300 PPM Max.
K:	50 PPM Max.		

TYPICAL PHYSICAL PROPERTIES

FISHER APS: 3.5 – 5 μm
SCOTT DENSITY: 16 - 25 g/in³
TAP DENSITY: 2.0 – 3.0 g/cm³
SIFTED MESH: - 250 mesh (Tyler) (< 63 microns)

All other elements are contained at <20 ppm.

All products are compliant with EU RoHS Directive 2002/95/EC.

Data Sheet - Molybdenum MOD Metal Sales Powder

LS/rv-4/2007

CHP-WEB PAGE VERSION-OCTOBER 2006